

IPS d.SIGN®

Oksidiranje (program 21)

Firing parameters for the oxide firing of IPS d.SIGN 96

T	B	S	t [#]	H	V ₁	V ₂
950°C 1742°F	403°C 757°F	1 min. 1 min.	60°C 108°F	5 min. 5 min.	450°C 842°F	950°C 1742°F



Prije pečenja



Nakon pečenja



1. pečenje opaquera (wash firing) (program 22)



Firing parameters for the 1st opaquer firing
(wash firing)

T	B	S	t [#]	H	V ₁	V ₂
900°C 1652°F	403°C 757°F	6 min. 6 min.	80°C 144°F	1 min. 1 min.	450°C 842°F	889°C 1632°F

Prije pečenja



Nakon pečenja



* prvi sloj opaquera je najrjeđiji i nanosi se u tankom sloju

* nakon svakog pečenja isprati vaporom

2. pečenje opaquera (program 23)

Firing parameters for the 2nd opaquer firing

T	B	S	t [#]	H	V ₁	V ₂
890°C 1634°F	403°C 757°F	6 min. 6 min.	80°C 144°F	1 min. 1 min.	450°C 842°F	889°C 1632°F

Prije pečenja



Nakon pečenja



* drugi sloj je gušći i deblji od prvog, moguće je samo djelomično prosijavanje metala



* greška – ako je opaquer rijedak, tekućina brzo ishlapi i pojavi se pukotina. Ispravak – običnim dijamantom prebrusi se i namaže se zadnji sloj

3. pečenje opaquera (program 23)

Firing parameters for the 2nd opaquer firing

T	B	S	t [*]	H	V ₁	V ₂
890°C 1634°F	403°C 757°F	6 min.	80°C 144°F	1 min.	450°C 842°F	889°C 1632°F

Prije pečenja





Nakon pečenja



* treći sloj isti je kao i drugi sloj

* metal nakon trećeg sloja ne smije prosijavati



* opaquer je O.K. ako se sjaji kao ljuška jajeta

1. pečenje Deep Dentin, Dentin/Body i Incisal (program 24)

Firing parameters for the 1st dentin and incisal firing

T	B	S	t _✓	H	V ₁	V ₂
870°C 1508°F	403°C 757°F	4-9 min. 4-9 min.	60°C 108°F	1 min. 1 min.	450°C 842°F	869°C 1506°F



* bijeli prah – Deep Dentin

* roza prah – Dentin/Body


Deep Dentin



Dentin/Body



Nakon pečenja



Incisal




2. pečenje Dentin/Body i Incisal (program 24)


Firing parameters for the 2nd dentin and incisal firing

T	B	S	t _✓	H	V ₁	V ₂
870°C 1598°F	463°C 757°F	4-9 min. 108°F	60°C 108°F	1 min.	450°C 842°F	860°C 1598°F

Prije pečenja



Nakon pečenja



Nakon obrade



Pečenje glazure (pasta) (program 25)

Firing parameters for glaze firing with glazing material

T	B	S	t ↘	H	V ₁	V ₂
830°C 1526°F	403°C 757°F	4 min.	60°C 108°F	1-2 min. 1-2 min.	450°C 842°F	829°C 1524°F



Kraj

